

Illustration on polyamide

0,4 %

Characteristics

C. I.	Mixture
CAS No.	-
Chemical class	Metal complex azodye

Properties


Solubility (g/l at 25°C)	50
--------------------------	----

Fastness

	polyamide		
standard depth	1/3		
Light Xenotest		4	
	polyamide		
standard depth	1/3		
Water	3-4	4-5	4-5
Washing 40°C	4	4-5	4-5
Perspiration acid	4	4-5	4-5
Perspiration alkaline	4	4-5	4-5

Application possibilities

Exhaustion dyeing - polyamide ●



● suitable ◐ partially suitable ○ unsuitable