

Illustration on wool / on polyamide

0,5%	0,9%

Characteristics

C. I.	Acid Yellow 220
C. I. No.	11714
CAS No.	-
Chemical class	Metal complex azodye


Properties

Solubility (g/l at 25°C)	70
--------------------------	----


Fastness	wool						polyamide	
<i>standard depth</i>	1/25	1/12	1/6	1/3	1/1	2/1	1/1	2/1
Light Xenotest	5-6	6	6-7	7	7-8	7-8	6-7	7
	wool							
<i>standard depth</i>	1/1							
Water	4-5		4-5		4-5			
Crabbing	3-4		4-5		4-5			
Washing 40°C	3-4		5		5			
Washing 60°C	2-3		3-4		5			
Perspiration acid	4-5		4-5		4-5			
Perspiration alkaline	4-5		4-5		4			
Rubbing dry					4-5			
Hot pressing wet after 4 h	4				5			
Milling acid	4		4-5		5			
Milling alkaline	3-4		3-4		5			
Crossdyeing neutral	3		1		4-5			
Potting	3-4		1-2		4-5			
Decatizing	4							
Dry cleaning	4							
	polyamide							
<i>standard depth</i>	1/1							
Water	4-5		4-5		4-5			
Sea water	4-5		4-5		4-5			
Washing 40°C	3-4		5		5			
Washing 60°C	2-3		4-5		5			
Perspiration acid	4-5		4-5		4-5			
Perspiration alkaline	4-5		4-5		4-5			
Rubbing dry					5			
Hot pressing wet after 4 h	4		4-5		4-5			
Swimming bath water	3D							
Dry cleaning	4-5							
Nitrogen oxides	4-5							
Dry heat 150°C	4		4-5		4-5			

Application possibilities

Exhaustion dyeing - wool ●



Exhaustion dyeing - polyamide ●



Testing methods

Fastness	
Light Xenotest	ISO 105-B02-1994
Water	ISO 105-E01-1994
Washing 40°C	ISO 105-C01-1989
Washing 60°C	ISO 105-C03-1989
Sea water	ISO 105-E02-1994
Swimming bath water	ISO 105-E03-1994
Perspiration	ISO 105-E04-1994
Rubbing	ISO 105-X12-1987
Hot pressing	ISO 105-X11-1994
Milling acid	ISO 105-E14-1994
Milling alkaline	ISO 105-E12-1989
Potting	ISO 105-E09-1989
Crabbing	ISO 105-E08-1994
Crossdyeing neutral	ISO 105-X07-1994
Decatizing	ISO 105-E10-1994
Dry cleaning	ISO 105-D01-1993
Nitrogen oxides	ISO 105-G01-1993
Dry heat	ISO 105-P01-1993
The fastness figures in the tables mean:	
fastness to light	other fastness properties
1 - very poor	1 - poor
2 - poor	2 - moderate
3 - moderate	3 - fairly good
4 - fairly good	4 - good
5 - good	5 - very good
6 - very good	
7 - excellent	
8 - unsurpassed	
The letters indicate the following changes in shade:	
R - redder	D - duller
Bl - bluer	Br - brighter
Y - yellower	S - stronger
G - greener	W - weaker
The numbers at individual dye fastness data mean:	
First number	- change in shade
Second number	- staining on the undyed adjacent fabric which is of the same material as the tested sample
Third number	- staining on the undyed adjacent fabric