

Illustration on bleached sulphite pulp


Characteristics

C. I.	Mixture
CAS No.	-

Properties

Light Xenotest	4
Waste water colouring	4-5
Specific weight [g/cm ³]	1,08

Application possibilities

Dyeing in Mass	●
----------------	---

Application possibilities

Acid sizing	
	x % Spoloxyl dye
	2 % Hercat 2511
	4 % alluminium sulphate

Testing methods

Fastness to light	Xenotest ISO 105-B02
<i>The fastness figures in the tables mean:</i>	
1 - very poor	5 - good
2 - poor	6 - very good
3 - moderate	7 - excellent
4 - fairly good	8 - unsurpassed
Waste water colouring	
<i>The numbers at the individual dye fastness data mean against grey scale</i>	
1 - stains strongl	4 - stains slightl
2 - stains medium	5 - colourless
3 - stains a little	